



RingLock Standard Lid 146 mm

Product no: 382 Round Shape:



DIMENSIONS

External diameter: 145.4 mm ± 1 mm Height: $8.9 \text{ mm} \pm 0.5 \text{ mm}$

WEIGHT

Weight: 13.6 g ± 1.4 g

PERFORMANCE

Stacking tests The stacking tests have been performed to the standard virgin raw material as stated below at 23°C over a

period of 2 months. Stackability depends on many factors and the above data is meant as an indication only.

Consequently, customers should make internal trials to dertermine the viability of stacking and transportation.

CLOSURE SYSTEM

Peel-off Closure type:

DECORATION

Decoration available: IML

RAW MATERIAL

PP Raw material options:

Masterbatch colours: Colours according to Superfos standard selected pantone colours.

Hot temperatures: The material chosen has a very good heat resistance and the packaging is suitable for hot filling. Notably,

plastic packaging become flexible when subjected to hot filling temperatures and care must be taken in relation to stacking immediately after hot filling. The Superfos packaging must be tested by the customer with

the actual product before approval for use at hot temperatures.

Cold temperatures: Freezing conditions require special resins available on request. The Superfos packaging must be tested by

the customer with the actual product before approval for use at low temperatures.

QUALITY SPECIFICATIONS

Approvals: All Superfos Products comply with the European Union Commission Regulation No. 10/2011/EC with

> amendments, relating to materials and articles intended to come into contact with food, unless otherwise stated. In accordance with EU legislation, it is the responsibility of the customer to ensure that the supplied

product is suitable for the intended use.

Shelf life: The compliance of the product to the technical specifications in this data sheet is guaranteed for 12 months

after the date of the delivery subject to suitable storage. Suitable storage include protection of e.g. direct sun

light, rain, very low temperatures or very high temperatures over a long period.

Quality information: Deviations in the product specifications in this data sheet of 0.025% or less (i.e. 25 items per 100,000) are

considered acceptable in the industry and therefore cannot be construed as a defect. Also, please refer to the

Standard Sales and Delivery Terms in force at the time of delivery.

Specifications are subject to change without notice. Latest revision: 24-08-2022 www.superfos.com