Berry Superfos		Technical Datasheet
UN SuperFlex Standard Lid 317 mm		
Product no: 486 UN Shape: Round		
DIMENSIONS		
External diameter:	320.3 mm ± 3 mm Height:	24.2 mm ± 0.5 mm
WEIGHT		
Weight:	114 g ± 5.7 g	
PERFORMANCE		
UN approval:	UN Group 3 solids with inside bag	
Stacking tests	The stacking tests have been performed to the standard virgin raw material as stated below at 23°C over a period of 2 months. Stackability depends on many factors and the above data is meant as an indication only. Consequently, customers should make internal trials to dertermine the viability of stacking and transportation.	
CLOSURE SYSTEM		
Closure type:	Flex-off	
DECORATION		
Decoration available:	None	
RAW MATERIAL		
Raw material options:	PP	
Masterbatch colours:	Colours according to Superfos standard selected pantone colours.	
Hot temperatures:	The material chosen has a very good heat resistance and the packaging is suitable for hot filling. Notably, plastic packaging become flexible when subjected to hot filling temperatures and care must be taken in relation to stacking immediately after hot filling. The Superfos packaging must be tested by the customer with the actual product before approval for use at hot temperatures.	
Cold temperatures:	Freezing conditions require special resins available on request. The Superfos packaging must be tested by the customer with the actual product before approval for use at low temperatures.	
QUALITY SPECIFICATIONS		
Approvals:	All Superfos Products comply with the European Union Commission Regulation No. 10/2011/EC with amendments, relating to materials and articles intended to come into contact with food, unless otherwise stated. In accordance with EU legislation, it is the responsibility of the customer to ensure that the supplied product is suitable for the intended use.	
Shelf life:	The compliance of the product to the technical specifications in this data sheet is guaranteed for 12 months after the date of the delivery subject to suitable storage. Suitable storage include protection of e.g. direct sun light, rain, very low temperatures or very high temperatures over a long period.	
Quality information:	Deviations in the product specifications in this data sheet of 0.025 considered acceptable in the industry and therefore cannot be co Standard Sales and Delivery Terms in force at the time of delivery	nstrued as a defect. Also, please refer to the
www.superfos.com	Specifications are subject to change without notice.	Latest revision: 31-01-2018