



SuperLift Standard Lid 240 mm

Product no: 4056 Shape: Round



DIMENSIONS

External diameter: 234.4 mm ± 1 mm Height: $13.6 \text{ mm} \pm 0.5 \text{ mm}$

WEIGHT

Weight: $44 g \pm 4 g$

PERFORMANCE

Stacking tests The stacking tests have been performed to the standard virgin raw material as stated below at 23°C over a period of 2 months. Stackability depends on many factors and the above data is meant as an indication only.

Consequently, customers should make internal trials to dertermine the viability of stacking and transportation.

CLOSURE SYSTEM

Peel-off Closure type:

DECORATION

Decoration available: Dry Offset Decoration area offset: 185 mm

RAW MATERIAL

Raw material options: PP

Masterbatch colours: Colours according to Superfos standard selected pantone colours.

Hot temperatures: The material chosen has a very good heat resistance and the packaging is suitable for hot filling. Notably,

plastic packaging become flexible when subjected to hot filling temperatures and care must be taken in relation to stacking immediately after hot filling. The Superfos packaging must be tested by the customer with

the actual product before approval for use at hot temperatures.

Freezing conditions require special resins available on request. The Superfos packaging must be tested by Cold temperatures:

the customer with the actual product before approval for use at low temperatures.

QUALITY SPECIFICATIONS

Approvals: All Superfos Products comply with the European Union Commission Regulation No. 10/2011/EC with

amendments, relating to materials and articles intended to come into contact with food, unless otherwise

stated. In accordance with EU legislation, it is the responsibility of the customer to ensure that the supplied

product is suitable for the intended use.

Shelf life: The compliance of the product to the technical specifications in this data sheet is guaranteed for 12 months

after the date of the delivery subject to suitable storage. Suitable storage include protection of e.g. direct sun

light, rain, very low temperatures or very high temperatures over a long period.

Deviations in the product specifications in this data sheet of 0.025% or less (i.e. 25 items per 100,000) are Quality information:

considered acceptable in the industry and therefore cannot be construed as a defect. Also, please refer to the

Standard Sales and Delivery Terms in force at the time of delivery.

www.superfos.com Specifications are subject to change without notice. Latest revision: 09-11-2017